

### Print carrier

**JAC® STICK** is a glossy, special PVC film featuring inherent adhesive properties. It sticks to smooth surfaces without any need for an adhesive.

Examples of application:  
For high quality durable signs, that need to be simple to apply and easy to remove and reuse. Advertising on storefront windows, decoration, lettering with interchangeable characters, protection of delicate surfaces.

**Offset-printed:** with both purely oxidative drying and UV-curing inks, which are resistant to plasticiser and suitable for films and  
**Screen-printed:** with conventional (i.e. solvent-based) and UV-curing inks

For technical guidance please visit our web side under Downloads "Guidelines for use" – Offset printing

JAC® STICK 87015 – transparent  
JAC® STICK 87215 – white

### Average values

Type No.	87015	87215
Weight (g/m <sup>2</sup> )	195	195
Thickness (µm)	150	150
Service Temperature (°C)	-20 up to + 70	
Application Temperature (°C)	≥ +5	≥ +5
Shelf life of laminate (years) <sup>1)</sup>	1	1
Max. outdoor durability (years) <sup>2)</sup>	1	1

<sup>1)</sup>Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2 °C and a relative humidity of 50 % ± 5 %.

<sup>2)</sup>Under normal climatic conditions as prevailing in Central Europe.

For information regarding EHS regulation please visit our web side under downloads "Guidelines for Use" 5.12 Product Compliance Jac Screen

### Adhesion

No need for adhesive.

### Average values

	JAC STICK
Adhesion (FTM 1) (N/25 mm) 24 hrs Glass	0.05
Recommended minimum application temperature (°C)	> +5
Heat resistance up to 24 hrs (°C)	+70
Resistance to cold (°C) down to	-20

### Silicone paper

**Z 250** is a PE-coated medium-weight board with excellent handling and feeding properties.  
**Only available with JAC® STICK**

### Average values

	Z 250
Weight (g/m <sup>2</sup> )	215
Thickness (µm)	320

#### Warranty and liability

Issued June 2015

All Avery Dennison and JAC® statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and JAC® products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison and JAC® products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2015 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.  
This issue replaces all previous issues.

